

Technical Data Sheet of Chloroprene Rubber 213

Chemical Name: Chloroprene Rubber 213

CAS NO.: 9010-98-4

Technical Data of DCR213:

Items	Specifications		
Mooney Viscosity (ML 100°C₁₊₄)	DCR 2131	DCR 2132	DCR 2133
	35-45	46-55	According to customer needs
Mooney Scorch (MSt₅, min)	14		12
Tensile Strength, ≥Mpa	12		12
Modulus at 500%, Mpa	2-7		5-8
Elongation at break, ≥%	700		650
Volatile matter, ≤%	1.5		1.5
Appearance	Milk brown chips		

Application:

For making dust covers, highway and bridge vibration cushions, seals and other products of low temperature application.

Package:

Packed in paper bags, 25kg net each

Storage:

Keep under cover in a cool and well-ventilated place, avoiding direct sunlight.

The shelf life is one year below 20°C and half a year below 30°C from the date of production.